



Endutex - Revestimentos Têxteis sa
Mrs. Clara Ribeiro
Rua da Baiona 22
4795-784 VILARINHO STS
Portugal

your notice of

your ref.

our ref.
JW/443

date
Zwijnaarde, 2014-02-18


Comments on report 13.02396.02

Dear,

Like defined in the harmonized standard EN 14041 'Resilient, textile and laminate floor coverings - Essential characteristics': If a claim for slip resistance is made, the floor covering intended to be used in dry and non-contaminated conditions shall have a dynamic coefficient of friction of $> 0,30$ when tested ex-factory under dry conditions in accordance with EN 13893 and shall be declared as technical class DS.

We determined the dynamic coefficient of friction on samples Endutex supplied us:
T1307729: printfloor

	μ = dynamic coefficient of friction	
	direction of production	perpendicular to the direction of production
printfloor	$\mu = 0.68$	$\mu = 0.73$



addressee
Mrs. Clara Ribeiro

our ref.
JW/443

date
2014-02-18

page number
2

Conclusions:

The product printfloor fulfilled the criteria like mentioned in the harmonized standard to be declared as technical class DS.



We hope having been helpful with this information.

Kind regards,

A handwritten signature in black ink, appearing to read 'Wynendaele', written over a horizontal line.

Dr. Jo Wynendaele

Consultant Floor and Wall coverings